
















– other cuttings on request

TO 3 	TO 3 M 	TO 3/4 	
TOP 3 	TOP 3/1 	TOP 3 PF 	TO 218 Multiwatt 
TO 220 	TO 247 	TO 247/1 	TO 3158 
4 x TO220 	TO 126 	SOT 32 	TO 3159 

Thermally conductive foil made of siliconelastomer

foil type	foil WS	foil WG	foil WK	foil WB
material	silicone foil, standard	silicone foil, GF reinforced	silicone foil, GF reinforced, one-sided self-adhesive	silicone foil, GF reinforced

Washer

	WS 3	WG 3	WK 3	WB 3
TO-3	WS 3 M			
TO-3 M	WS 3/4		WK 3/4	
TO-3/4	WS 3 P	WG 3 P	WK 3 P	WB 3 P
TO-3 PF	WS 3158		WK 3158	WB 3158
3158	WS TOP 3			
TOP 3	WS TOP 3/1		WK TOP 3/1	
TOP 3/1		WG 218		
TO 218 (Multiwatt)	WS 247		WK 247	
TO 247	WS 220	WG 220	WK 220	WB 220
TO 220	WS 4 220			
4 X TO 220	WS 3159		WK 3159	WB 3159
3159			WK 126	
TO 126			WK 32	
SOT 32	WS 247/1			
TO 247/1				

Insulating tube

TO-220 Ø 11 mm, length 25 mm	WSC-220			
TO-3 PF Ø 13.5 mm, length 25 mm	WSC-3 P			
TO-247 Ø 14.5 mm, length 30 mm	WSC-247			

Insulating tube as meterpiece

TO-220 Ø 11 mm	WSM-220			
TO-3 PF Ø 13.5 mm	WSM-3 P			

Tape material (width)

24 mm			WKT 24	
30 mm	WST 30			WBT 30
36 mm	WST 36			
85 mm	WST 85			
300 mm		WGT 300	WKT 300	WBT 300

	Foil WS	Foil WG	Foil WK	Foil WB
material thickness	0.3 mm	0.2 mm		0.15 mm
material hardness	75 Shore A	87 Shore A		90 Shore A
dielectric strength	10 kV	6.5 kV		3 kV
thermal resistance	0.4 K/W	0.42 K/W	0.45 K/W	0.34 K/W
thermal conductivity	1.22 W/m·K	1.13 W/m·K	0.92 W/m·K	1.43 W/m·K
insulation resistance	2.9·10 ¹⁵ Ω·cm	5.7·10 ¹⁵ Ω·cm		1.6·10 ¹⁵ Ω·cm
extensibility	100 %	2 %		4 %
temperature range	-60°C... +180°C			
class of flammability	UL 94 V-0			